



Balcan Plastics Limited
 9340 Meaux Montréal, QC H1R 3H2 - Canada
 Tel.: +1. 514.326.9130 - www.balcan.com



Div. of Balcan Plastics Ltd
First Film Extruding (Div. of Balcan Plastics Ltd.)
 1320 Route 9 Champlain, NY 12919 - USA
 Tel.: 1.877.422.5226 - www.ffebpl.com

Revision Date: March 07, 2019

TECHNICAL DATASHEET

CUSTOMER NAME: DELROC INDUSTRIES LTD.
PRODUCT TYPE: VAPOR BARRIER, CGSB 10 MIL SHEETING
PRODUCT DESCRIPTION: 240" x 100' x 2000 10MIL, NATURAL
PRODUCT/ITEM#: CUST#21142, ITEM#05V90211 – CGSB

PROPERTIES		UNITS	TEST METHODS	TYPICAL VALUES	TOLERANCES
Description				240" x 100' x 2000	
Formulation				LDPE & LLDPE	
Gauge (average)		mil	ASTM D 2103	10.00	+/- 10%
Coefficient of Friction			ASTM D 1894	HIGH	0.10 to 0.35
Color				Natural	
Print				YES (LOGO CGSB)	
Water Vapour Permeance		Ng/Pa.s.m ²	ASTM E-96	1.1	Max. 15
Dart Impact		grams	ASTM D 1709	480	Min. 300
Tensile Strength	MD	PSI	ASTM D 882	3,470	Min. 1740
	TD			3,300	Min. 1160
Tensile Elongation	MD	%	ASTM D 882	800	Min. 225
	TD			900	Min. 350
Treatment			BPP 03	No	
Shrink		%	Balcan	---	
Induction Time		Min (190°C)	ASTM D 3895	> 30	Min. 30 (spec. minimum of CGSB)

Properties listed above are typical values as measured by Balcan Plastics. The determination of suitability and fitness for use is the sole responsibility of the buyer and user.

Balcan Plastics and First Film Extruding make no representation or warranty of any kind, express or implied, with respect to this product, whether as to merchantability, fitness for particular purpose or otherwise.